



## Vistex® 175 Anti-Fog Film

### DESCRIPTION

Anti-Fog coated polyester film, designed to be a multiple use anti-fog film for inexpensive facemasks and visors. Available in three thicknesses (2, 4 and 7 mil). Can be soaked in water repeatedly without losing anti-fog properties.

### FEATURES

- Permanent Anti-Fog Protection
- Optical clarity
- Hydrophilic
- Designed for Roll-to-Roll Application

### CONTACT INFORMATION

**FSI Coating Technologies**  
**Corporate Office - N.A.**  
 45 Parker, Suite 100  
 Irvine, California 92618 USA  
 Tel: +1-949-540-1140  
 Fax: +1-949-540-1150  
 technicalsupport@fsicti.com

**SDC Technologies - Americas**  
**Corporate Headquarters**  
 45 Parker, Suite 100  
 Irvine, CA 92618 USA  
 800-272-7681 (Toll Free USA)  
 Tel: +1-714-939-8300  
 technicalsupport.ca@sdctech.com

**SDC Technologies - Europe**  
 Unit 7, Avondale Industrial Estate  
 Pontrhydryn Cwmbran  
 NP44 1UG, Great Britain  
 Tel: +44-1633-627030  
 technicalsupport.eu@sdctech.com

**SDC Technologies - China**  
 1585 Gumei Road  
 Xuhui District  
 Shanghai 200233  
 China  
 Tel: +86-21-61517768  
 customercare.cn@sdctech.com

**SDC Technologies Asia Pacific Pte. Ltd.**  
 27 Tuas South Street 1  
 Singapore 638035  
 Tel: +65-6210-6355  
 customercare.ap@sdctech.com

[fsicti.com](http://fsicti.com)

### FILM PROPERTIES

PROPERTY	TYPICAL VALUES
Thickness	2, 4 or 7 mil
Appearance	Clear and colorless
Visible Light Transmission	90%
Tear Strength (initial)	
2 mil	1.9 kg (4.2 lbs)
4 mil	3.8 kg (8.4 lbs)
7 mil	5.1 kg (11.2 lbs)
Anti-fog (TM-153)	Pass

### ANTI-FOG PROPERTIES

Vistex 175 Film is hydrophilic which causes condensation to spread as a clear layer, rather than form droplets which appear as fog. Although it absorbs moisture, the coating does not dissolve in water, so it will not smudge when wet. It prevents or reduces fogging under all temperature/humidity conditions, even after extended immersion in water or repeated cleanings. Where scratch resistance is critical please contact an FSICT representative for information on Visgard® products.

### CARE AND STORAGE INSTRUCTIONS

Treated surfaces may be cleaned with an ammonia-free glass cleaner and a sponge, tissue or paper towel. Cleaners containing alcohol may be used but the alcohol content should be <30%. Do not use cleaners which contain moisturizers, abrasives, strong acids, or caustic substances. Remove any oily contamination with a grease cutting cleaner. Vistex film should be stored in an environmentally controlled area with relative humidity of less than 60%.

### WARRANTY AND LIABILITY LIMITATIONS

Typical lead-time for shipment of Vistex 175 Film is six to eight (6 - 8) weeks from confirmation of a purchase order. FSI provides several shipping options. Please contact an FSI representative to determine which option best fits your needs. All orders are shipped ex works/ F.O.B. Additional shipment charges including customs clearance and fees (if applicable) are the responsibility of the customer.

©2020 FSI Coating Technologies, Inc. All rights reserved. FSI Coating Technologies is a wholly-owned subsidiary of SDC Technologies, Inc. Vistex® and Visgard® are registered trademarks of FSI Coating Technologies, Inc